

Product Name: Muriate of Potash - Granular

SGN: **285**

Uniformity Index: **50**

Order Code: GRA

MSDS No.: 1

Source: Saskatchewan / New Brunswick

Alternate Names: Potassium Chloride, KCI, Potash, MOP

page 1 of 1

| CHEMICAL COMPOSITION | UNIT | RANGE | TYPICAL | GUARANTEE |
|--------------------------------------|------|-------------|---------|-----------|
| Potassium Oxide, as K ₂ 0 | % | 60.0 - 60.7 | 60.4 | 60.0 min. |
| Moisture, as H ₂ 0 | % | 0.05 - 0.20 | 0.10 | |
| Potassium Chloride, as KCl | % | | 95.60 | |
| Potassium, as K | % | | 50.14 | |
| Magnesium, as Mg | % | | 0.04 | |
| Calcium, as Ca | % | | 0.04 | |
| Sodium Chloride, as NaCl | % | | 3.56 | |
| Chloride, as Cl | % | | 47.68 | |
| Sulfate, as SO ₄ | % | | 0.08 | |
| Sodium, as Na | % | | 1.40 | |
| Insolubles in water | % | | 0.45 | |

| PARTICLE SIZE, PERCENT CUMULATIVE | | | | | | |
|-----------------------------------|---------|------|----------|---------|--|--|
| TYLER MESH | OPENING | UNIT | RANGE | TYPICAL | | |
| +5 | 4.00 mm | % | 0 - 5 | 3 | | |
| +6 | 3.35 mm | % | 20 - 40 | 28 | | |
| +7 | 2.80 mm | % | 40 - 70 | 52 | | |
| +8 | 2.36 mm | % | 65 - 85 | 75 | | |
| +9 | 2.00 mm | % | 85 - 98 | 93 | | |
| +10 | 1.70 mm | % | 95 - 100 | 97 | | |

| PHYSICAL PROPERTIES | | | | |
|-------------------------|--------------------|---------------|--|--|
| Bulk Density | kg/m³ | 1,041 - 1,201 | | |
| | lb/ft ³ | 65 - 75 | | |
| Angle of Repose | degrees | 32° | | |
| Uniformity Index | | 50 | | |
| Size Guide Number (SGN) | | 285 | | |
| Color | | Red/Pink | | |

| GUARANTEED ANALYSIS |
|---|
| (0-0-60) |
| Soluble Potash (K ₂ O) - 60% |

Note: All of the above properties are based on the analysis of a composite sample from a bulk shipment. Grab samples or individual car samples may fall outside of the specified typical.

